

COLLECTION: **FOCUS**

DESIGN: **FOCUS**

FABRIC SPECIFICATIONS

Composition	63% Recycled Polyester, 37% Polyester	Average yarn number	16.67
Construction	14.17x14.17	Woven	Yes
Useable width cm	302	Useable width inch	118.9
Full width cm	304	Full width inch	119.69
Weight g/m ²	170	Thickness mm	0.640
Colouring type	Piece dyed	Filament or staple	52% staple + 48% filament
Textured or non textured	52% not textured + 48% textured		

CARE AND USAGE

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains

Yes

Curtains and draperies

Yes

ENVIRONMENTAL STANDARDS



STANDARD 100
2111231
Centexbel



Prop 65

Yes

FR STANDARDS

AATCC 96 Complies	No	ASNZS 1530.2 Pass	Yes
British BS 5867 part 2 type B	Yes	Canadian ULC S109 large flame	Yes
Canadian ULC S109 small flame	Yes	European EN 13773	No
MVSS 302	Yes	IMO FTPC part 7 drapery	No
French NF P 92-503 507	No	French NF P 92-504 507	No
French NF P 92-505 507	No	American NFPA 701 2010	Yes

COLLECTION: **FOCUS**

DESIGN: **FOCUS**

MECHANICAL PERFORMANCE

AATCC 96 - 165°F / 74°C - Complies	No	Colour fastness to light	4-5
Acoustic absorption ISO 354 - ISO 11654	D		

Colour fastness to light - ISO 105-B02

Colour fastness to light	4-5
--------------------------	-----

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Tearing strength - ISO 13937-3

Tearing strength warp N	96	Tearing strength weft N	97
-------------------------	----	-------------------------	----

Tensile strength - ISO 13934-1

Tensile strength warp N/5cm	560	Tensile strength weft N/5cm	960
-----------------------------	-----	-----------------------------	-----

Elongation - ISO 13934-1

Elongation warp %	20.5	Elongation weft %	25
-------------------	------	-------------------	----

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	-0.02	Dimensional change weft	-0.14
Dimensional change warp after ironing without steam	0.00	Dimensional change weft after ironing without steam	0.07
Dimensional change warp after ironing with steam	-0.47	Dimensional change weft after ironing with steam	-0.67