

Technical product specifications for this design

COLLECTION: INTEGRA

DESIGN: INTEGRA



CARE CODES



CARE AND USAGE

Care code comments

Iron on reverse side

Use codes

Upholstery
Accessories

Yes
Yes

Bed covering

Yes

ENVIRONMENTAL STANDARDS



STANDARD
100
2111231
Centexbel



Labels

GRS post-consumer

Yes

Prop 65

Yes

COLLECTION: INTEGRA

DESIGN: INTEGRA

FR STANDARDS

British BS 5852 source 0	Yes	British BS 5852 source 1	Yes
British BS 5852 source 1 note	Yes, with FR coating	American CAL 117	Yes
European EN 1021 part 1 and 2	Yes	European EN 1021 note	Yes, with FR coating
MVSS 302	Yes	American NFPA 260	Yes

FABRIC SPECIFICATIONS

Composition	95% Recycled Polyester, 5% Polyurethane	Average yarn number	22.73
Composition fabric	100% Recycled Polyester	Composition backing	90% Recycled Polyester, 10% Polyurethane
Construction	65x35	Useable width cm	140
Useable width inch	55.12	Full width cm	142
Full width inch	55.91	Weight g/m ²	440
Thickness mm	1.460	Colouring type	Printed
Filament or staple	100% Filament	Textured or non textured	100% Not textured
Knitted	Yes		

Treatment

Backing	Yes
---------	-----

Type of finish

There are no technical details for this section.

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Plain	Yes
-------	-----

COLLECTION: INTEGRA

DESIGN: INTEGRA

MECHANICAL PERFORMANCE

Wear resistance for coated fabrics	90,000	Colour fastness to light	5
Wyzenbeek double rubs	100,000	Pilling	5
Brush pilling	5	Blocking resistance	1
Flexing endurance	25,000	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	100,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	5
--------------------------	---

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	5
-------------------------	---

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	5
-------------------------	---

Colour fastness to wear – ISO 12947-2

There are no technical details for this section.

Tearing strength – ISO 13937-3

Tearing strength warp N	83	Tearing strength weft N	71
-------------------------	----	-------------------------	----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	980	Tensile strength weft N/5cm	950
-----------------------------	-----	-----------------------------	-----

Elongation – ISO 13934-1

Elongation warp %	43,5	Elongation weft %	116
-------------------	------	-------------------	-----

Seam slippage – ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

COLLECTION: INTEGRA

DESIGN: INTEGRA

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	0.00	Dimensional change warp after ironing with steam	0.00
Dimensional change warp after ironing without steam	0.00	Dimensional change weft	0.00
Dimensional change weft after ironing with steam	0.20	Dimensional change weft after ironing without steam	0.00

WASHABILITY

Resistance to domestic washing 30° C, indicated in % – ISO 6330

Dimensional change warp	-0.50	Dimensional change warp after ironing	-0.40
Dimensional change weft	-0.70	Dimensional change weft after ironing	-0.66
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % – ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % – ISO 6330

Dimensional change warp	-1.79	Dimensional change warp after ironing	-1.79
Dimensional change weft	-1.69	Dimensional change weft after ironing	-1.59
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % – ISO 105 D01

Dimensional change warp	-0.89	Dimensional change warp after ironing	-0.79
Dimensional change weft	-0.93	Dimensional change weft after ironing	-0.79
Colour fastness ISO 105 D01	5		

COLLECTION: INTEGRA

DESIGN: INTEGRA

CONSTRUCTION

Yarn 1

Warp Composition	100% Post recycled Polyester	Warp Is Filament	No
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	105D	Warp Textured	No
Warp Threads per cm	65	Warp TPM	0

Yarn 2

Weft Composition	100% Post recycled Polyester	Weft Is Filament	No
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	75D	Weft Textured	No
Weft Threads per cm	35	Weft TPM	0

DOWNLOADS

-  [Integra-Cal TB 117-2013-43207](#)
-  [Integra FP 24120662B Bru Textiles BS 5852 Source 0+1](#)
-  [Integra-FMVSS302-43207](#)
-  [Integra-NFPA 260 UFAC-43207](#)
-  [Integra FP 24120662A Bru Textiles EN 1021-1 & EN 1021-2](#)