



Composition Composición	80.82% PVC Phthalate free PVC libre de ftalatos 19.18% Polyester Poliéster
Width Ancho	1.37 m 1.50 yd
Weight Peso	730 g/m ² 51.5 oz/yd ²
Length of rolls Longitud de las piezas	30 m 32.8 yd
Finish Acabado	Sanitized-Actifresh® Embossed Gofrado
UPF	50+ AZ/NZS 4399/1996
Water column Columna de agua	>10.000 mm DIN EN 20811
Tear resistance Resistencia al desgarro	Warp Urdimbre 25 N Weft Trama 25 N ISO 4674 - 1
Tensile strength Resistencia a la tracción	Warp Urdimbre 350 N Weft Trama 300 N ISO 1421 1
Vinyl adhesion Adherencia del vinilo	Warp Urdimbre 20 N Weft Trama 20 N ISO 2411
Elongation/deformation Elongación/deformación	Warp Urdimbre 25% min/10% max Weft Trama 50% min/18% max SAE J855
Abrasion resistance Resistencia a la abrasión	>400.000 Martindale DIN EN ISO 12947-2:2016 >50.000 Wyzenbeek CFFA 1A
Oil resistance Resistencia a aceites	No change Sin cambio DIN 53 359
Cold impact Impacto en frío	No cracks Sin Grietas FLTM BN 128-01
Flame resistance Resistencia a la llama	DIN 4102 B2 Önorm B 3825 Group 1 EN 1021 Parts 1 & 2 UNI 9175 Class 1/IM ÖNORM A 3800 Part 1 Class Q1 SAE J369/MVSS302 100mm/min. max IMO-MSC-307(88) (FTP code 2010) Annex 1 Part 8 FAR 25/853 Appendix F Part I 10" FED-STD-191A Test 5903 6 in max.
COLOUR FASTNESS SOLIDEZ DEL COLOR	
To light A la Luz	6/8 UNE EN ISO 105-B02:2014
To sea water Al agua marina	4-5/5 DIN EN ISO 105-E02
To chlorinated water Al agua clorada	4/5 UNE EN ISO 105-E03:2010
To artificial saliva A saliva artificial	5/5 DIN 53 160 - 1
To artificial sweat A sudor artificial	5/5 DIN 53 160-2
To perspiration A la transpiración	4-5/5 DIN EN ISO 105 E - 04
To rubbing Al frote	Dry Seco 5.0 in AATCC Wet Húmedo 5.0 in AATCC UNE EN ISO 105-X12:2016
Thermal aging Envejecimiento térmico	4/5 LP - 463LB - 13 - 01
Cleaning instructions Manutención	 Use neutral soap Utilizar jabón neutro

Uses Usos



Qualities Calidades



Sensitive values of tolerance +/- 7%. Valores susceptibles de tolerancia de +/- 7%.

5 YEARS WARRANTY

The Agora warranty covers the fabric becoming unserviceable as a result of loss of colour or strength from normal exposure conditions, including sunlight, mildew, rot and atmospheric chemicals, when properly installed, used and maintained. The warranty does not cover labour and installation costs supplied by the dealer. The warranty neither applies against deterioration of any kind due to abusive use, accidental burns, negligence or perforations.

La garantía Agora cubre un anormal deterioro del tejido debido a la pérdida de color o resistencia siempre que existan unas condiciones de exposición normales, incluyendo el sol, moho, putrefacción y químicos de la atmósfera en general, siempre y cuando el tejido haya sido instalado, utilizado y mantenido correctamente. La garantía no cubre los trabajos de instalación del distribuidor. La garantía tampoco cubre, en cualquier caso, el deterioro debido al uso abusivo, quemaduras accidentales, negligencia o perforación.