

COLLECTION: BUDGET BUSTER

DESIGN: BUST

BASIC INFORMATION

Brand	Fabric Library Dubai	Number of colour ways	3
Tariff item number	5407920000	MID	CNSUZFUR88SUZ
Country of origin	China	Characteristics	Texture
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	0
Full roll diameter inch	0	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE CODES



CARE AND USAGE


Use codes

Upholstery	Yes	Accessories	Yes
------------	-----	-------------	-----

ENVIRONMENTAL STANDARDS



STANDARD 100
0611045
Centexbel



Labels

There are no technical details for this section.

FR STANDARDS

BS 5852 Source 0	Yes	CAL 117	Yes
FMVSS 302	Yes	NFPA 260	Yes

COLLECTION: BUDGET BUSTER

DESIGN: BUST

FABRIC SPECIFICATIONS

Composition	75% Polyester, 25% Viscose	Average yarn number	21.92
Composition backing	100% Polyester	Construction	36x28
Woven	Yes	Useable width cm	145
Useable width inch	57.09	Full width cm	147
Full width inch	57.87	Weight g/m ²	292
Thickness mm	0.000	Colouring type	Piece dyed
Water repellent	Yes	Filament or staple	60% Filament, 40% Staple
Textured or non textured	100% Textured		

Treatment

Backing Yes

Type of finish

There are no technical details for this section.

Type of print or dye

Disperse Yes

Weaving type

Plain Yes

COLLECTION: BUDGET BUSTER

DESIGN: BUST

MECHANICAL PERFORMANCE

Martindale rubs	30,000	Colour fastness to light	4
Wyzenbeek double rubs	63,800	Pilling	3-4
Brush pilling	4	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	63,800	Wyzenbeek cotton duck type heavy upholstery	Yes
Water repellent	Yes	Wyzenbeek wire screen medium duty	Yes

Colour fastness to light - ISO 105-B02

Colour fastness to light	4
--------------------------	---

Colour fastness to weathering - ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength - ISO 13937-3

Tearing strength warp N	72	Tearing strength weft N	76
-------------------------	----	-------------------------	----

Tensile strength - ISO 13934-1

Tensile strength warp N/5cm	800	Tensile strength weft N/5cm	650
-----------------------------	-----	-----------------------------	-----

Elongation - ISO 13934-1

Elongation warp %	33	Elongation weft %	26
-------------------	----	-------------------	----

Seam slippage - ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.00	Dimensional change warp after ironing with steam	0.00
Dimensional change warp after ironing without steam	0.00	Dimensional change weft	0.00
Dimensional change weft after ironing with steam	0.00	Dimensional change weft after ironing without steam	0.00

COLLECTION: BUDGET BUSTER

DESIGN: BUST

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-2.03	Dimensional change warp after ironing	-1.66
Dimensional change weft	-1.39	Dimensional change weft after ironing	-0.86
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

Dimensional change warp	-2.72	Dimensional change warp after ironing	-2.25
Dimensional change weft	-1.56	Dimensional change weft after ironing	-1.06
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-4.75	Dimensional change warp after ironing	-4.32
Dimensional change weft	-2.99	Dimensional change weft after ironing	-2.86
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.86	Dimensional change warp after ironing	-0.13
Dimensional change weft	-0.20	Dimensional change weft after ironing	-0.13
Colour fastness ISO 105 D01	4-5		

COLLECTION: BUDGET BUSTER

DESIGN: BUST

CONSTRUCTION


Yarn 1

Warp Composition	60% Polyester, 40% Viscose	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	600D	Warp Textured	Yes
Warp Threads per cm	36	Warp TPM	0

Yarn 2

Weft Composition	60% Polyester, 40% Viscose	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	600D	Weft Textured	Yes
Weft Threads per cm	28	Weft TPM	0

DOWNLOADS

 [BUST-NFPA 260_UFAC-41418](#)

 [BUST-FMVSS302-41418](#)

 [BUST-Cal TB 117-2013-41418](#)

