

COLLECTION: BUDGET BUSTER

DESIGN: FRIDAY

### BASIC INFORMATION

Brand	Fabric Library Dubai	Number of colour ways	6
Tariff item number	5407520000	MID	CNSUZFUR88SUZ
Country of origin	China	Characteristics	Texture
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	0
Full roll diameter inch	0	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

### CARE CODES



### CARE AND USAGE


#### Use codes

Upholstery	Yes	Accessories	Yes
------------	-----	-------------	-----

### ENVIRONMENTAL STANDARDS



**STANDARD 100**  
0611045  
Centexbel



#### Labels

Prop 65	Yes
---------	-----

### FR STANDARDS

BS 5852 Source 0	Yes	CAL 117	Yes
FMVSS 302	Yes	NFPA 260	Yes

COLLECTION: BUDGET BUSTER

DESIGN: FRIDAY

## FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	15.36
Construction	36x21	Woven	Yes
Useable width cm	145	Useable width inch	57.09
Full width cm	147	Full width inch	57.87
Weight g/m <sup>2</sup>	371	Thickness mm	1.450
Colouring type	Piece dyed	Water repellent	Yes
Filament or staple	100% filament	Textured or non textured	100% textured

### Treatment

---

Backing	Yes
---------	-----

### Type of finish

---

There are no technical details for this section.

### Type of print or dye

---

Disperse	Yes
----------	-----

### Weaving type

---

Dobby	Yes
-------	-----

COLLECTION: BUDGET BUSTER

DESIGN: FRIDAY

## MECHANICAL PERFORMANCE

Martindale rubs	40,000	Colour fastness to light	3-4
Wyzenbeek double rubs	100,000	Pilling	4
Brush pilling	5	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	100,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Water repellent	Yes	Wyzenbeek wire screen heavy duty	Yes

### Colour fastness to light - ISO 105-B02

Colour fastness to light	3-4
--------------------------	-----

### Colour fastness to weathering - ISO 105-B04:1994

There are no technical details for this section.

### Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

### Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

### Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

### Tearing strength - ISO 13937-3

Tearing strength warp N	83	Tearing strength weft N	120
-------------------------	----	-------------------------	-----

### Tensile strength - ISO 13934-1

Tensile strength warp N/5cm	1800	Tensile strength weft N/5cm	1100
-----------------------------	------	-----------------------------	------

### Elongation - ISO 13934-1

Elongation warp %	37	Elongation weft %	27
-------------------	----	-------------------	----

### Seam slippage - ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

### Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.00	Dimensional change warp after ironing with steam	-0.07
Dimensional change warp after ironing without steam	-0.13	Dimensional change weft	0.00
Dimensional change weft after ironing with steam	0.13	Dimensional change weft after ironing without steam	-0.07

COLLECTION: BUDGET BUSTER

DESIGN: FRIDAY

## ACOUSTICS

### Sound absorption performance for drapery

There are no technical details for this section.

### Sound absorption performance for upholstery

There are no technical details for this section.

### Sound transmission

There are no technical details for this section.

## WASHABILITY

### Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-1.49	Dimensional change warp after ironing	-1.26
Dimensional change weft	-0.30	Dimensional change weft after ironing	-0.40
Colour fastness ISO 105 C06	4-5		

### Resistance to domestic washing 40° C, indicated in % - ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

### Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-3.46	Dimensional change warp after ironing	-3.33
Dimensional change weft	-0.57	Dimensional change weft after ironing	-2.59
Colour fastness ISO 105 C06	4-5		

### Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

### Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-3.31	Dimensional change warp after ironing	-0.33
Dimensional change weft	-0.27	Dimensional change weft after ironing	-0.33
Colour fastness ISO 105 D01	4-5		

COLLECTION: BUDGET BUSTER

DESIGN: FRIDAY

## CONSTRUCTION



### Yarn 1



Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	380D	Warp Textured	Yes
Warp Threads per cm	36	Warp TPM	0

### Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	380D	Weft Textured	Yes
Weft Threads per cm	21	Weft TPM	0

## DOWNLOADS

-  [Friday BS 5852 Source 0](#)
-  [FRIDAY-NFPA 260\\_UFAC-41423](#)

-  [FRIDAY-Cal TB 117-2013-41423](#)
-  [FRIDAY-FMVSS302-41423](#)

